WO 00/75389 PCT/AU00/00630



- 12 -

ABSTRACT OF THE DISCLOSURE

A solid oxide fuel cell system component that may be exposed to an oxidizing atmosphere within the system is formed from a heat resistant allow that preferably has a wt% composition of Al 5-0, Si 0.1-3.8, Mn ≤ 0.5, Cu ≤ 0.23, Ni ≤ 0.61, C ≤ 0.02, P ≤ 0.04, S ≤ 0.04, Cr < 5, and residue Fe excluding incidental impurities. Preferably the component can function at temperatures exceeding about 750°C.